De polyvalente dakbaan met een bewezen duurzaamheid van meer dan 40 jaar en volledig recycleerbaar

NO ROOF TO WASTE

DERBIGUM® SP (FM)

- DERBIGUM SP is composed of a blend made of a specific bitumen modified by noble polymers (high-grade APP also called TPO) & two distinct reinforcements, fiberglass & non-woven polyester.
- The specificity of the blend & the raw materials chosen ensures its durability & fire resistance.
- The fiberglass sees to its perfect dimensional stability and heat & UV resistance.
- The non-woven polyester cares for its resistance to impacts & tearing.





Technische kenmerken

Vloeiweerstand	EN 1110	MLV	≥ 140	°C
Soepelheid bij lage temperatuur	EN 1109	MLV	≤ -15	°C
Trekweerstand L/D	EN 12311-1	MLV	500 x 450	N/50mm
Breukrek bij maximale treksterkte L/D	EN 12311-1	MLV	40 x 40	%
Dimensionele stabiliteit	EN 1107-1	MLV	≤ 0.20	%
Nageldoorscheursterkte L/D	EN 12310-1	MLV	≥ 150	N

MLV : Manufacturer Limited Value
MDV : Manufacturer Determined Value
*BDA = Bureau Dak Advies

Specifieke eigenschappen

- **Factory Mutual FM Global-certificering** (afhankelijk van de configuratie van het waterdichtingscomplex)
- Polyvalent gebruik, onderhoudsvriendelijk, volledig recycleebaar
- **Bewezen duurzaamheid > 40 jaar**

DERBIGUM®

DERBIGUM NEDERLAND B.V.
Postbus 3270 - 4800 DG Breda
Veldsteen 52 - 4815 PK Breda
Tel. 015 215 40 00 – Fax 015 215 40 11
E-mail: infonl@derbigum.com

Productinformatie

Dikte	EN 1849-1	MDV (±2,0)	4	mm
Lengte	EN 1849-1	MLV	7.27	m
Breedte	EN 1848-1	MLV	1.10	m
Oppervlakte		MLV	8	m^2
Rolgewicht		MDV (±2,0)	36	kg
Aantal rollen /pallet			25	

Bewaring

Rolls must be carried and stored in a vertical position. The floor must be regular and free of sharped objects.

Dit document annuleert en vervangt elk vorig gepubliceerd document. - 06/06/2023 - ID2541

DERBIGUM NEDERLAND B.V.
Postbus 3270 - 4800 DG Breda
Veldsteen 52 - 4815 PK Breda
Tel. 015 215 40 00 – Fax 015 215 40 11
E-mail: infonl@derbigum.com